

Description

The 4901 *Sn99 No Clean Solder Wire* is an electronic grade solder wire. It uses a high-purity, eutectic Sn99.3/Cu0.7 alloy, which is complemented with a no clean, synthetically refined, splatter-proof resin flux core. The 4901 solder meets J-STD-004B, ASTM B 32, and exceeds J-STD-006C specifications.

This solder is a great lead-free alternative to leaded solders. It is suitable, less costly replacement for SAC305.

The 4901 solders achieve a consistent solder and flux percentage through a state-of-the-art, extrusion, wire-drawing machine. This machine continually monitors the wire to prevent voids and ensure consistency, providing a top-grade solder wire.

Benefits & Features

- **Eutectic alloy** (liquidus = solidus temperature)
- **Alloy exceeds J-STD-006C and meets ASTM B 32 purity requirements**
- **Flux meets J-STD-004B**
- **The resin spreads like rosin-activated flux**
- **Virtually non-splattering**
- **Non-corrosive**
- **Non-conductive residue**
- **Halide free**
- **Suitable for Use in Food Facilities as a Non-Food Chemical**—Canadian and NFS recognition letters available on request

COMPLIANCE

- ✓ Dobb Frank ([DRC conflict free](#))
- ✓ REACH ([compliant](#))
- ✓ RoHS ([compliant](#))

Wire Sizes Availability

<i>Cat No.</i>	<i>Std. Wire Gauge</i>	<i>Diameter</i>		<i>Packaging</i>	<i>Sizes</i>
4901	21	0.81 mm	0.032 in	Spool	¼, ½, 1 lb, or 2 lb

General Flux Parameters

<i>Properties</i>	<i>Value</i>
Residue Removal Flux Percentage Flux feature Shelf life	Not required 2.2% Wets and spreads like a RA type flux and virtually non-splattering. 5 y

Continued on the next page

Flux Core Properties

The synthetically refined resin wets and spreads like a RA flux. This no clean flux is virtually non-spattering. It gives rise to a hard, non-conductive and non-corrosive residue.

Physical Properties	Method	Value
Flux Classification	J-STD-004B EN29454-1	RELO Type 1.1.3 Resin
Flux Type		Low
Flux Activity		<0.05%
Halides %(wt)		Lightly opaque
Solid Flux Color	Visual	24 °C [75 °F]
Softening Point of Flux Extract		190–210
Acid Number (mgKOH/g sample)	IPC-TM-650 2.3.13	No removal
Copper Mirror	IPC-TM-650 2.3.32	Pass
Silver Chromate—Chlorides + Bromides	IPC-TM-650 2.3.33	130 mm ²
Solder Spread	IPC-TM-650 2.4.46	Pass
Flux Residue Dryness	IPC-TM-650 2.4.47	0.30%
Spitting of Flux-Cored Wire Solder	IPC-TM-650 2.4.48	Non-corrosive
Corrosion Test	IPC-TM-650 2.6.15	2.3 × 10 ¹¹ Ω
Surface Insulation Resistance (SIR)	IPC-TM-650 2.6.3.3	6.1 × 10 ¹¹ Ω
Bellcore (Telecordia)	Bellcore GR-78-CORE 13.1.3	Pass
Electromigration	Bellcore GR-78-CORE 13.1.4	55%
Post Reflow Residue	TGA Analysis	Optional
Cleaning Requirements	—	

Sn99.3/Cu0.7/Co Alloy Typical Literature Properties

Physical Properties	Value ^{a)}
Color	Silvery-white metal
Density @26 °C [78 °F]	7.4 g/cm ³
Tensile Strength	22 N/mm ² [3 100 lb/in ²]
Elongation	41%
Shear Strength	~23 N/mm ² [~3 300 lb/in ²]
Hardness, Brinell	9HB
Electrical Properties	Value
Volume Resistivity	12.3 μΩ·cm
Electrical Conductivity ^{b)}	13% IACS

a) N/mm² = mPa; lb/in² = psi;

b) International Annealed Copper Standard: 100% give 5.8 × 10⁷ S/m.

Continued on the next page

Continued...

Thermal Properties	Value
Melting Point, Solidus	227 °C [442 °F]
Melting Point, Liquidus	227 °C [442 °F]
Tip Temperature Upper Limit	Do not exceed 400 °C [752 °F]
Coefficient of Thermal Expansion (CTE) ^{c)}	23.5 ppm/°C
Thermal Conductivity	~82 W/(m·K)
Specific Heat Capacity	~294 J/(kg·K)

NOTE: This table present typical literature values for Sn99.3/Cu0.7 alloys.

c) CTE for pure tin; unit conversions: ppm/°C = $\mu\text{m}/(\text{m}\cdot\text{K}) = \text{in}/\text{in}/^\circ\text{C} \times 10^{-6} = \text{unit}/\text{unit}/^\circ\text{C} \times 10^{-6}$

Solder Alloy Composition

Properties	Value	Properties	J-STD-006C
MAIN INGREDIENTS	COMPOSITION	IMPURITIES ^{a)}	REQUIREMENTS
Sn	99.3%	Sb	≤0.20% Max
Cu	0.7%	Ag	≤0.10% Max
		Bi	≤0.10% Max
		In	≤0.10% Max
		Pb	≤0.10% Max
		Au	≤0.05% Max
		As	≤0.03% Max
		Fe	≤0.02% Max
		Ni	≤0.01% Max
		Al	≤0.005% Max
		Zn	≤0.003% Max
		Cd	≤0.002% Max

a) Meets the requirements of J-STD-006C and meets ASTM B 32.

Storage

Protect from direct heat or sunlight. Store between 18 to 27 °C [65 to 80 °F].

Cleaning

The flux residue does not need to be removed for typical applications. If removal is desired, a solvent system like the *MG 4140* can be used. For best results, warm the cleaning solution to about 40 °C [104 °F].

Health and Safety


Please see the 4901 **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Health and Safety: Avoid breathing fumes. Wash hands thoroughly after use. Do not ingest.

HMIS® RATING

HEALTH:	* 1
FLAMMABILITY:	0
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Form</i>	<i>Packaging</i>	<i>Net Weight</i>	
4901-112G	Solid wire	Pack of 25	113 g	0.25 lb
4901-227G	Solid wire	Pack of 3	227 g	0.5 lb
4901-454G	Solid wire	Spool	454 g	1.0 lb
4901-2LB	Bar	Bar	908 g	2.0 lb



Sn99 No Clean Solder Wire

4901 Technical Data Sheet

ISO 9001:2008 Registered Quality System. Burlington, Ontario, CANADA SAI Global File: 004008

4901

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+(1) 905-331-1396 (International)

+(44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.