

Ferrite Components for the Electronics Industry


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 5678140921 Printed: 2013-07-03









Part Number: 5678140921

Frequency Range: Dimensions

Description: 78 POT CORE

Application: **Inductive Components** 

Where Used: Closed Magnetic Circuit

Part Type: Pot Cores

Generic Name: P14/8

## **Mechanical Specifications**


Weight: 3.200 (g) per Set

# Part Type Information

P9/5S, P11/7S, P14/8, P18/11, P22/13, P26/16, P30/19, P36/22

Pot cores have found application in all types of inductive devices. The core configuration provides a high degree of self-shielding. It also facilitates gapping to enhance utility for a variety of magnetic designs.

- -Pot cores can be supplied with the center post gapped to a mechanical dimension or an AL value.
- -AL value is measured at 1 kHz, B < 10 gauss.
- -Weight indicated is per pair or set.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 5678140921 Printed: 2013-07-03









# **Mechanical Specifications**

Dim	mm	mm	nominal	inch
		tol	inch	misc.
Α	14.00	±0.3	0.551	-
В	4.20	±0.2	0.165	-
С	9.55	±0.3	0.376	-
D	3.10	±0.2	0.122	-
Е	11.80	±0.4	0.465	-
F	5.90	±0.2	0.232	-
G	3.30	±0.6	0.130	-
Н	2.90	±0.3	0.114	-
J	-		-	-
K	-	-	-	-

## **Electrical Specifications**

Typical Impedance ( $\Omega$ )				
Electrical Properties				
A <sub>L</sub> (nH)	1950 ±25%			
Ae(cm <sup>2</sup> )	0.25100			
$\Sigma$ l/A(cm <sup>-1</sup> )	7.90			
I <sub>e</sub> (cm)	1.98			
V <sub>e</sub> (cm <sup>3</sup> )	0.49500			
A <sub>min</sub> (cm <sup>2</sup> )	.198			

## **Land Patterns**

V	W	Χ	Υ	Z
-	-	-	-	-

# Winding Information

Turns	Wire	1st Wire	2nd Wire
Tested	Size	Length	Length
-	-	-	-

## **Reel Information**

Tape Width	Pitch			
mm -	mm -	Reel -	Reel -	Reel -

## Package Size

Pkg Size
-
(-)

## Connector Plate

# Holes	# Rows
-	-

#### Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

∠I/A - Core Constant

A<sub>e</sub>: Effective Cross-Sectional Area

 $A_1$  - Inductance Factor  $\left(\frac{L}{N^2}\right)$ 

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 5678140921 Printed: 2013-07-03







# **Ferrite Material Constants**


Compressive Strength ...... 42 kgf/mm<sup>2</sup>

Young's Modulus ...... 15x10<sup>3</sup> kgf/mm<sup>2</sup>

Specific Gravity ......  $\approx 4.7 \text{ g/cm}^3$ 

The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A MnZn ferrite specifically designed for power applications for frequencies up to 200 kHz.

RFID rods, toroids, U cores, and E&I cores are all available in 78 material.

Fair-Rite Product's Catalog Part Data Sheet, 5678140921

Printed: 2013-07-03








#### 78 Material Characteristics:


Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		$\mu_{i}$	2300
Flux Density	gauss	В	4800
@ Field Strength	oersted	н	5
Residual Flux Density	gauss	B,	1500
Coercive Force	oersted	H <sub>c</sub>	0.20
Loss Factor	10-6	tan δ/μ	4.5
@ Frequency	MHz		0.1
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		1.0
Curie Temperature	°C	T <sub>c</sub>	>200
Resistivity	Ωcm	ρ	2x10²

## Complex Permeability vs. Frequency




Measured on an 18/10/6mm toroid using the HP 4284A and the HP 4291A.

#### Initial Permeability vs. Temperature




Measured on an 18/10/6mm toroid at 100kHz.

#### Incremental Permeability vs. H



#### **Hysteresis Loop**




Measured on an 18/10/6mm toroid at 10kHz.

# Fair-Rite Products Corp. Your Signal Solution®

Ferrite Components for the Electronics Industry


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

#### Amplitude Permeability vs. Flux Density



Measured on an 18/10/6mm toroid at 10kHz.

#### Power Loss Density vs. Temperature



Measured on an 18/10/6mm toroid using the Clarke Hess 258 VAW.


Fair-Rite Product's Catalog Part Data Sheet, 5678140921

Printed: 2013-07-03






#### Power Loss Density vs. Flux Density



Measured on an 18/10/6mm toroid using the Clarke Hess 258 VAW at 100°C

## Flux Density vs. Temperature



Measured on an 18/10/6 mm toroid at 10kHz and H=5 oersted.