


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 3061990891 Printed: 2013-07-03







| Part Number: | 3061990891 |
|------------------|--|
| Frequency Range: | Low Permeability, 61 (ui=125) material |
| Description: | 61 ROD |
| Application: | Inductive Components |
| Where Used: | Open Magnetic Circuit |
| Part Type: | Antenna/RFID Rods |
| Mechanical Sn | acifications |

Mechanical Specifications

Weight: 3.300 (g)

Part Type Information

These rods are designed for use in antenna and RFID transponder applications. Rods are available in three materials to cover a frequency range from 50 kHz to 25 MHz. Suggested frequency ranges: 78 material < 200 kHz, 61 material 0.2 -5.0 MHz and 61 material > 5.0 MHz.

-See www.fair-rite.com/newfair/catalog_rodinfo.htm graphs for temperature information for these rods.

-Rods can be supplied with a Parylene C coating. Parylene coated rods have a '4' as the last digit. Parylene C is RoHS compliant.

-For any rod requirement not listed here, feel free to contact our customer service group for availability and pricing.

-The Antenna/RFID Kit (part number 0199000024) contains a selection of these rods.

-Explanation of Part Numbers: Digits 1&2 = product class, 3&4 = material grade, the last digit 1 = uncoated rod and <math>4 = Parylene coated rod.

Fair-Rite Products Corp. Your Signal Solution®

Ferrite Components for the Electronics Industry

Fair-Rite Products Corp. PO Box J.One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com Fair-Rite Product's Catalog Part Data Sheet, 3061990891 Printed: 2013-07-03



Mechanical Specifications

| Dim | mm | mm | nominal | inch |
|-----|-------|-------|---------|-------|
| | | tol | inch | misc. |
| А | 5.00 | ±0.04 | 0.197 | - |
| В | - | - | - | - |
| С | 35.00 | ±0.80 | 1.378 | - |
| D | - | - | - | - |
| E | - | - | - | - |
| F | - | - | - | - |
| G | - | - | - | - |
| Н | - | - | - | - |
| J | - | - | - | - |
| К | - | - | - | - |

Electrical Specifications

| Typical Impedance (Ω) | | |
|-----------------------|---------|--|
| | | |
| Electrical Properties | | |
| U _{ROD} | 24 | |
| Ae(cm ²) | 0.19600 | |

Land Patterns

| \vee | W | Х | Y | Z |
|--------|-----|---|---|---|
| | ref | | | |
| - | - | - | - | - |
| - | - | - | - | - |

Winding Information

| Turns | Wire | 1st Wire | 2nd Wire |
|--------|------|----------|----------|
| Tested | Size | Length | Length |
| - | - | - | - |

Reel Information

| Tape Width | Pitch | Parts 7 " | Parts 13 " | Parts 14 " |
|------------|-------|-----------|------------|------------|
| mm | mm | Reel | Reel | Reel |
| - | - | - | - | - |

Package Size

| Pkg Size |
|----------|
| - (-) |
| |

Connector Plate

| # Holes | # Rows |
|---------|--------|
| - | - |

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

I/A - Core Constant

A_e: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\left(\frac{L}{N^{2}}\right)$

N/AWG - Number of Turns/Wire Size for Test Coil

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns




Fair-Rite Product's Catalog Part Data Sheet, 3061990891 Printed: 2013-07-03



Ferrite Material Constants

| Specific Heat | 0.25 cal/g/ºC |
|--|--|
| Thermal Conductivity | 3.5 - 4.5 mW/cm - °C |
| Coefficient of Linear Expansion | 8 - 10x10 ⁻⁶ /ºC |
| Tensile Strength | 4.9 kgf/mm ² |
| Compressive Strength | 42 kgf/mm ² |
| Young's Modulus | 15x10 ³ kgf/mm ² |
| Hardness (Knoop) | 650 |
| Specific Gravity | \approx 4.7 g/cm ³ |
| The above quoted properties are typical for Fair-Rit | e MnZn and NiZn ferrites. |

See next page for further material specifications.




Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com


A high frequency NiZn ferrite developed for a range of inductive applications up to 25 MHz. This material is also used in EMI applications for suppression of noise frequencies above 200 MHz.

EMI suppression beads, beads on leads, SM beads, wound beads, multi-aperture cores, round cable snap-its, rods, antenna/RFID rods, and toroids are all available in 61 material.

Strong magnetic fields or excessive mechanical stresses may result in irreversible changes in permeability and losses.



Measured on a 19/10/6mm toroid using the HP 4284A and the HP 4291A.




Fair-Rite Product's Catalog Part Data Sheet, 3061990891 Printed: 2013-07-03



61 Material Characteristics:


| Property | Unit | Symbol | Value |
|---|---------|--------|-------------------|
| Initial Permeability @ B < 10 gauss | | μ | 125 |
| Flux Density | gauss | в | 2350 |
| @ Field Strength | oersted | н | 15 |
| Residual Flux Density | gauss | B, | 1200 |
| Coercive Force | oersted | Hc | 1.8 |
| Loss Factor | 10-6 | tanδ/μ | 30 |
| @ Frequency | MHz | | 1.0 |
| Temperature Coefficient of Initial Permeability (20 -70°C) | %/°C | | 0.10 |
| Curie Temperature | °C | Tc | >300 |
| Resistivity | Ωcm | ρ | 1x10 ⁸ |

Percent of Original Impedance vs. Temperature



Measured on a 2661000301 using the HP4291A.

Hysteresis Loop



Measured on a 19/10/6mm toroid at 100kHz.

Measured on a 19/10/6mm toroid at 10kHz.