

Ferrite Components for the Electronics Industry


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com





Fair-Rite Product's Catalog Part Data Sheet. 9478203002





Part Number: 9478203002

Frequency Range: Dimensions

Description: 78 PLANAR E CORE

Application: **Inductive Components**

Where Used: Closed Magnetic Circuit

Part Type: **Planar Cores**

Generic Name: EE22/11

Mechanical Specifications


Weight: 13.000 (g) per Set

Part Type Information

EE14/7, EE18/8, EE22/11, EE32/13, EE38/16, EE43/19. EE64/21, EI 14/5, EI 18/6, EI 22/7, EI 32/10, E 64/15, ER9.5, ER11, ER14.5

Planar EE cores, and Planar EI cores, with their low profile are suitable for board level installation allowing assembly without the need for plastic coilformers and can also allow windings integrated into multi-level PCBs. Planar ER cores with their low mass and low profile are suitable for Surface Mount installations in low power filter and transformer applications.

- -Planar EE, ER and EI cores can be supplied with the center post gapped to a mechanical dimension or an AL value.
- -AL value is measured at 1 kHz, B < 10 gauss.
- -Weight indicated is per pair or set.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Fair-Rite Product's Catalog Part Data Sheet, 9478203002 Printed: 2013-07-03









Mechanical Specifications

Dim	mm	mm	nominal	inch
		tol	inch	misc.
Α	21.80	± 0.4	0.858	
В	5.70	± 0.2	0.224	-
С	15.80	± 0.35	0.622	-
D	3.20	± 0.2	0.126	-
E	16.80	± 0.4	0.661	-
F	5.00	± 0.2	0.197	-
G	-	-	-	-
Н	-		-	-
J	-		-	-
K	-	-	-	-

Electrical Specifications

Typical Impedance (Ω)				
Electrical Properties				
A _L (nH)	4500 ±25%			
Ae(cm ²)	0.79000			
Σ I/A(cm ⁻¹)	4.10			
I _e (cm)	3.24			
V _e (cm ³)	2.56000			
A _{min} (cm ²)	.790			

Land Patterns

V	W ref	X	Υ	Z
-	-	-		

Winding Information

Turns	Wire	1st Wire	2nd Wire
Tested	Size	Length	Length
-	-	-	-

Reel Information

Tape Width	Pitch	Parts 7 "	Parts 13 "	Parts 14 "
mm	mm	Reel	Reel	Reel
-	-	-	-	-

Package Size

Pkg Size
-
(-)

Connector Plate

# Holes	# Rows
-	-

Legend

+ Test frequency

Preferred parts, the suggested choice for new designs, have shorter lead times and are more readily available.

The column H(Oe) gives for each bead the calculated dc bias field in oersted for 1 turn and 1 ampere direct current. The actual dc H field in the application is this value of H times the actual NI (ampere-turn) product. For the effect of the dc bias on the impedance of the bead material, see figures 18-23 in the application note How to choose Ferrite Components for EMI Suppression.

A ½ turn is defined as a single pass through a hole.

∠I/A - Core Constant

A_e: Effective Cross-Sectional Area

 A_{I} - Inductance Factor $\binom{L}{N2}$

I e: Effective Path Length

Ve: Effective Core Volume

NI - Value of dc Ampere-turns

N/AWG - Number of Turns/Wire Size for Test Coil



Fair-Rite Product's Catalog Part Data Sheet, 9478203002 Printed: 2013-07-03







Ferrite Material Constants

Specific Heat 0.25 cal/g/°C

Coefficient of Linear Expansion 8 - 10x10⁻⁶/°C

Tensile Strength 4.9 kgf/mm²


Compressive Strength 42 kgf/mm²

Young's Modulus 15x10³ kgf/mm²

Specific Gravity $\approx 4.7 \text{ g/cm}^3$

The above quoted properties are typical for Fair-Rite MnZn and NiZn ferrites.

See next page for further material specifications.



Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

A MnZn ferrite specifically designed for power applications for frequencies up to 200 kHz.

RFID rods, toroids, U cores, and E&I cores are all available in 78 material.

Fair-Rite Product's Catalog Part Data Sheet, 9478203002

Printed: 2013-07-03








78 Material Characteristics:


Property	Unit	Symbol	Value
Initial Permeability @ B < 10 gauss		μ	2300
Flux Density	gauss	В	4800
@ Field Strength	oersted	н	5
Residual Flux Density	gauss	B,	1500
Coercive Force	oersted	H _c	0.20
Loss Factor	10-6	tan δ/μ	4.5
@ Frequency	MHz		0.1
Temperature Coefficient of Initial Permeability (20 -70°C)	%/°C		1.0
Curie Temperature	°C	T _c	>200
Resistivity	Ωcm	ρ	2x10 ²

Complex Permeability vs. Frequency




Measured on an 18/10/6mm toroid using the HP 4284A and the HP 4291A.

Initial Permeability vs. Temperature




Measured on an 18/10/6mm toroid at 100kHz.

Incremental Permeability vs. H



Hysteresis Loop




Measured on an 18/10/6mm toroid at 10kHz.

Fair-Rite Products Corp. Your Signal Solution®

Ferrite Components for the Electronics Industry


Fair-Rite Products Corp. PO Box J,One Commercial Row, Wallkill, NY 12589-0288 Phone: (888) 324-7748 www.fair-rite.com

Amplitude Permeability vs. Flux Density



Measured on an 18/10/6mm toroid at 10kHz.

Power Loss Density vs. Temperature



Measured on an 18/10/6mm toroid using the Clarke Hess 258 VAW.


Fair-Rite Product's Catalog Part Data Sheet, 9478203002

Printed: 2013-07-03






Power Loss Density vs. Flux Density



Measured on an 18/10/6mm toroid using the Clarke Hess 258 VAW at 100°C

Flux Density vs. Temperature



Measured on an 18/10/6 mm toroid at 10kHz and H=5 oersted.